



Polyguard HBPU FG8448

SOLVENT FREE POLYURETHANE

Product Description

Polyguard HBPU FG8448 is a two-component, high-build, 100% volume solid polyurethane coating. It provides excellent durability, chemical resistance, aesthetic properties, gloss, and color retention for longer period of time. The component 'A' is a base consisting of superior-quality polyol and component 'B' is a curing agent.

Typical Uses

This coating system is designed for industrial exposures over prepared steel, wood, concrete, and plastic surfaces (with etching primer). It offers exceptional protection in marine applications, sewage and seawater tanks, pipes, and wastewater treatment facilities. It serves as a heavy-duty structural coating for moderately to severely corrosive environments, including sheet pilings, void spaces, chain lockers, steel mounting frames (i.e., base plate, uprights/columns, cross beams/braces, etc.) for solar panels, and liner for clarifiers.

Features

- Suitable for Solar Panel Frames
- Excellent scratch resistance
- Bio-bacterial resistance
- Superior corrosion resistance in severely corrosive environments
- Weatherproof protection for long-term outdoor performance
- Complies with AWWA C222 standard

Technical Properties

Color / Shades	All shades including black, grey, and off-white
Finish/ Gloss	Smooth & Glossy
Volume Solids	100%, mixed
Specific Gravity	1.13 Kg/Liter
Mix ratio	1:1 by volume
Typical Thickness	250-1000 microns [9.8-39.4 mils]
Coverage	2 m ² /liter at 500 microns WFT (theoretical)**
Flash Point (Typical)	220°C [428°F]
VOC	No measurable VOC level
Reducer/Thinner	Not applicable
Cleaner	Thinner C1

Drying Time	Surface Temperature	@ 25°C
Touch dry		1.5-2.5 Mins
Dry to handle		5-10 mins
Recoat		2 hours
Hard dry		4 Hours
Pot Life		15-20 Sec

If the maximum recoat time is exceeded, abrade the surface before recoating. The drying time depends on temperature, humidity, and film thickness. For NSF applications, it cures to service in 24 hours at 158°F (70°C).



Polyguard HBPU FG8448

SOLVENT FREE POLYURETHANE

Surface Preparation

All surfaces should be clean, dry, and free from contamination. They should also be assessed and treated in accordance with ISO 8504:2000.

Iron & Steel

Cleanliness: Blast cleaning to min. Sa 2½ (ISO 8501 1:2007).

Roughness: using abrasives suitable to achieve Grade, medium G (50 - 100 µm, Rz scale) (ISO 8503-2).

Galvanized Steel

The surface shall be sweep blast-cleaned with the nozzle angle at 45-60° from perpendicular at reduced nozzle pressure to create a sharp and angular surface profile using approved nonmetallic abrasive media. As a guide, a surface profile 25-55 µm, grade Fine G; Ry5 (ISO 8503-2) should be achieved.

Other surfaces

The coating may be used on other substrates. Please contact TRPL for more information.

Application

Application Method	Thinning	Application Parameters
Spray	-	Use multi components airless spray system with tip pressure 3000 to 4500 Psi or as per required visual surface and thickness of coating and with heating arrangement. Pressure at nozzle: 20 -32 MPa (200 to 320 bar) Nozzle tip sizes: 35-43 Thau depending on production rate Spray Angle: 90 ⁰ -110 ⁰
Brush & Roller	-	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness and uniformly coated surface with the repair material Polyguard RP FG8448 (3:1 by volume)

Thoroughly mix Comp. A (base) with Comp. B (hardener or curing agent) using an online static mixer. Ensure that the mixture is homogeneous before spraying. It is essential to achieve 100% ionization of the spraying film while maintaining the required application temperature.

System Cleaning: Be sure to flush the application equipment thoroughly with Thinner C1 both before and after use.

Filter Size & Cleaning Procedure: Filters should be removed, both in the pump & the spray gun after a certain frequency to avoid coating system choke up and filters recommended sizes shall be 60 and 80 mesh to smooth & trouble-free operations.

Note

- *To achieve a thickness of 2000 microns, it is advisable to use a two-pass approach.
- **The theoretical coverage will depend upon surface conditions & application skills. Allow appropriate loss factor.
- It is of vital importance that the nozzle and other parts including the static mixer of the spraying equipment are cleaned properly directly after the work is done due to the PU paint.
- The hoses should be used with high pressure of good quality and no longer than necessary.
- The hose length between the mixer & gun should be less than 1 meter.
- Preferably store both paint components at 20-25°C. Be aware that higher storage temperatures will shorten the life of the paint.
- For stripe/repair coating, however, a lower paint temperature may be favorable in order to get a sufficient pot life.



Polyguard HBPU FG8448 SOLVENT FREE POLYURETHANE

Application Conditions

The temperature of the substrate should be a minimum of 10°C and 5°C above the dew point of the air. Best coating adhesion is obtained by utilizing the induction time indicated after mixing the two components and a relative humidity of 85% during the application process. The temperature and the relative humidity should be measured in the vicinity of the substrate. Good ventilation is usually required. In the case of confined areas, ensure proper ventilation arrangements for drying. The coating should not be exposed to oil, chemicals, or mechanical stress until cured.

The coating should not be exposed to oil, chemicals, or mechanical stress until cured.

Packing

Base: 10 Liters & 200 Liters;
Hardener: 10 Liters & 200 Liters)

Storage

Shelf Life

12 Months, when sealed

Storage Conditions

Store indoors at 4.5°C [40°F] to 38°C [100°F]

The product must be stored in accordance with national regulations. Keep the containers in a cool and dry place and well-ventilated area with no direct source of heat or light. Containers must be kept tightly closed when not in use.

Safety: Handle with care. Before & during use, observe all safety labels on packaging and paint containers, consult Material Safety Data Sheets, and follow all local or national safety regulations. Avoid inhalation, avoid contact with skin & eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment. Apply only in well-ventilated areas.

Disclaimer: The information in this document is given to the best of TRPL's knowledge, based on laboratory testing & practical experience. TRPL products are considered semi-finished goods, as such products are often used beyond TRPL's control. TRPL can not guarantee anything but the quality of the product itself. Minor product variations may be implemented to comply with local requirements. TRPL reserves the right to change the given data without further notice. User should always consult TRPL for specific guidance on the general suitability of the product for their needs and specific application practices.